

(11)



Europäisches Patentamt

European Patent Office

Office européen des brevets

(12) Publication number:

0 092 918

B1

(12)

EUROPEAN PATENT SPECIFICATION

(5) Date of publication of patent specification: 19.10.88

(9) Int. Cl.⁴: A 61 K 9/22, A 61 K 47/00

(11) Application number: 83301856.7

(13) Date of filing: 31.03.83

Same as U.S. Patent 4,526,938

(14) Continuous release formulations.

(15) Priority: 22.04.82 GB 8211704

(16) Date of publication of application:
02.11.83 Bulletin 83/44

(17) Publication of the grant of the patent:
19.10.88 Bulletin 88/42

(18) Designated Contracting States:
AT BE CH DE FR GB IT LI LU NL SE

(19) References cited:
FR-A-2 373 279
GB-A-2 028 341
US-A-3 922 239

CHEMICAL ABSTRACTS, vol. 88, no. 12, 20th
March 1978, page 313, no. 79041n, Columbus,
Ohio, US; T.M.S. CHANG: "Biodegradable
semipermeable microcapsules containing
enzymes, hormones, vaccines, and other
biologicals" & J. BIOENG. 1976, 1(1), 25-32

(20) Proprietor: IMPERIAL CHEMICAL INDUSTRIES
PLC

Imperial Chemical House Millbank
London SW1P 3JF (GB)

(21) Inventor: Churchill, Jeffrey Richard
12 Chiltern Close
Sandiway Northwich Cheshire (GB)
Inventor: Hutchinson, Francis Gowland
29 Woodland Drive
Lymm Cheshire (GB)

(22) Representative: Atkinson, John David et al
Imperial Chemical Industries PLC
Legal Department: Patents
PO Box 6 Bessemer Road
Welwyn Garden City Hertfordshire, AL7 1HD
(GB)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European patent convention).

Description

This invention relates to pharmaceutical compositions of pharmacologically-active polypeptides, which provide continuous release of the polypeptide over an extended period when the composition is placed in an aqueous, physiological-type environment.

It has long been appreciated that the continuous release of certain drugs over an extended period following a single administration could have significant practical advantages in clinical practice, and compositions have already been developed to provide extended release of a number of clinically useful drugs, after oral dosing (see, for example, Remington's Pharmaceutical Sciences, published by Mack Publishing Company, Easton, Pennsylvania, U.S.A., 15th Edition, 1975, pages 1618—1631), after parenteral administration (*ibidem*, pages 1631—1643), and after topical administration (see, for example, United Kingdom Patent Number 1,351,409). A suitable method of parenteral administration is the subdermal injection or implantation of a solid body, for example a pellet or a film, containing the drug, and a variety of such implantable devices have been described. In particular, it is known that, for many drugs, suitable implantable devices for providing extended drug release may be obtained by encapsulating the drug in a biodegradable polymer, or by dispersing the drug in a matrix of such a polymer, so that the drug is released as the degradation of the polymer matrix proceeds.

Suitable biodegradable polymers for use in such sustained release formulations are well known, and include polyesters which gradually become degraded by hydrolysis when placed in an aqueous, physiological-type environment. Particular polyesters which have been used are those derived from hydroxycarboxylic acids, and much prior art has been directed to polymers derived from α -hydroxycarboxylic acids, especially lactic acids in both its racemic and optically active forms, and glycolic acid, and copolymers thereof — see, for example, United States Patents Numbers 3,773,919 and 3,887,699; Jackanicz *et al.*, Contraception, 1973, 8, 227—234; Anderson *et al.*, *ibidem*, 1976, 11, 375—384; Wise *et al.*, Life Sciences, 1976, 19, 867—874; Woodland *et al.*, Journal of Medicinal Chemistry, 1973, 16, 897—901; Yolles *et al.*, Bulletin of the Parenteral Drug Association, 1976, 30, 306—312; Wise *et al.*, Journal of Pharmacy and Pharmacology, 1978, 30, 686—689 and 1979, 31, 201—204.

United Kingdom Patent Specification Number 1,325,209 (equivalent to United States Patent Specification Number 3,773,919) and United States Patent Specification Number 3,887,669 make reference to extended or sustained release of polypeptides. The latter mentions insulin only, but it contains no specific example of any such formulation, and the reference to polypeptides is apparently entirely speculative, appearing, as it does, only in an extensive listing of very many different classes of drugs which can allegedly be incorporated into formulations of the kind described therein. In fact, essentially all of the other drug types referred to in that specification, apart from polypeptides, are relatively hydrophobic in character and of relatively low molecular weight, and the disclosure of that specification displays no recognition of the difficulties which we have encountered when seeking to obtain satisfactory sustained release formulations of polypeptides, many of which are relatively hydrophilic, and of relatively high molecular weight.

It is to be appreciated that "sustained" or "extended" release of a drug may be either continuous or discontinuous. We have now discovered, in fact, that in many cases when the teaching of the prior art, and in particular the teaching of United Kingdom Specification No. 1,325,209, is applied to the manufacture of a formulation of a polypeptide, the release of the polypeptide from the formulation, although occurring over an extended period of time, may also be discontinuous. For example, the release of a polypeptide from a polylactide polymer as described in the said Specification is often preceded by a significant induction period, during which no polypeptide is released, or is polyphasic, and comprises an initial period during which some polypeptide is released, a second period during which little or no polypeptide is released, and a third period during which most of the remainder of the polypeptide is released. By contrast, it is an object of the present invention to provide compositions of polypeptides from which, apart possibly from a relatively short initial induction period, the polypeptide is released continuously, with no periods during which little or no polypeptide is released. The words "continuous release" are used in this specification solely to describe a release profile which is essentially monophasic, although it may have a point of inflection, but certainly has no "plateau" phase.

United Kingdom Patent Specification Number 1,388,580 describes sustained release formulations containing insulin, which are based on hydrogels formed by reacting a water soluble polymer with a chelating agent, then cross linking the polymer-chelating agent chains by reaction with a polyvalent metal ion in aqueous solution to form a hydrogel. Insulin was incorporated in a preformed hydrogel in aqueous solution, and the whole was homogenised and injected sub-cutaneously or intramuscularly. EP—A—0067671 discloses sustained release compositions comprising an hydrogel which comprises at least one polymerisable cyclic (thio) ether.

It is an object of the present invention to provide an implantable or injectable pharmaceutical or veterinary formulation for pharmacologically useful polypeptides, which is in solid form, and which absorbs water from the animal body, after implantation, to form a hydrogel from which the polypeptide is released continuously over an extended period of time.

Thus, according to the present invention, there is provided a pharmaceutical composition comprising a pharmacologically useful polypeptide and a pharmaceutically or veterinarily acceptable amphipathic, non-

cross-linked linear, branched or graft block copolymer, which has a minimum weight average molecular weight of 5,000, in which the hydrophobic component is biodegradable or hydrolytically unstable under normal physiological conditions, and the hydrophilic component may or may not be biodegradable, the composition being capable of absorbing water to form a hydrogel when placed in water or an aqueous physiological type environment, but excluding such compositions in which the hydrophobic component is derivable from at least one cyclic (thio) ether.

This invention is applicable to polypeptides quite generally, without any limitation as to structure or molecular weight, but is most useful for polypeptides which are relatively hydrophilic, and the following list, which is not intended to be exhaustive, is indicative of polypeptides which may be employed in the formulation of this invention:—

oxytocin, vasopressin, adrenocorticotrophic hormone (ACTH), epidermal growth factor (EGF), prolactin, luteinizing hormone releasing hormone (LH—RH), growth hormone, growth hormone releasing factor, insulin, somatostatin, glucagon, interferon, gastrin, tetragastrin, pentagastrin, urogastrone, secretin, calcitonin, enkephalins, endorphins, angiotensins, renin, bradykinin, bacitracins, polymyxins, colistins, tyrocidin, gramicidines, and synthetic analogues and modifications and pharmaceutically-active fragments thereof, monoclonal antibodies and soluble vaccines.


A particular LH-RH analogue to which this invention is applicable is ICI.118,530, [Glu-His-Trp-Ser-Tyr-D-Ser(O-tBu)-Leu-Arg-Pro-Asp-Gly-NH₂].

By "an aqueous physiological type environment" we mean the body, particularly the musculature or the circulatory system, of a warm-blooded animal, although in laboratory investigations such an environment may be mimicked by aqueous liquids, optionally buffered to a physiological pH, at a temperature of between 35 and 40°C.

The continuous release composition of the invention may be placed in the body of an animal which it is desired to treat with a polypeptide by, for example, intramuscular or subcutaneous injection, or by subdermal surgical implantation, in conventional clinical or veterinary manner.

The pharmaceutically or veterinarily acceptable amphipathic copolymer may be, for example, a linear block copolymer of the formula $A_m(BA)_n$ or $B_m(AB)_n$, wherein m is 0 or 1, n is an integer, A is a pharmaceutically or veterinarily acceptable hydrophobic polymer and B is a pharmaceutically or veterinarily acceptable hydrophilic polymer, or the amphipathic copolymer may be a graft or branched block copolymer of the formula AB_n or BA_n , wherein A , B and n have the meanings stated above, and wherein respectively either a A or B is a backbone polymer with n units of a monomer or polymer B or A respectively grafted onto it.


The pharmaceutically or veterinarily acceptable hydrophobic polymer A may be, for example, poly-(D-, L- or DL-lactic acid), poly-(D-, L- or DL-lactide), polyglycolic acid, polyglycolide, poly-ε-caprolactone, poly(3-hydroxybutyric acid) or a non-therapeutic hydrophobic polypeptide, for example polybenzylglutamate. Alternatively, the hydrophobic polymer A may be a polyacetal of the general formula:



wherein R is a hydrocarbon radical.




represents two alkyl radicals or a cycloalkyl ring, and n is an integer, or a polycarbonate or polyorthoester of the general formula:



wherein R is a hydrocarbon radical, the arcuate dotted line represents a hydrocarbon linking group and n is

an integer, as described in United States Patent Number 4,093,709, or it may be a copolymer comprising such acetal, carbonate, or ortho-ester units alternating with diol units, or it may be a copolymer of the formula:



which is obtained by reacting pentaerythritol with ketene to form 3,9-bis(methylene)-2,4,8,10-tetraoxa-spiro[5.5]undecane which is then copolymerised with a diol HO—R—OH, as described in Journal of Polymer Science, Polymer Letters, 1980, pages 619—624. The diol HO—R—OH may be, for example, a high molecular weight polyethylene glycol or a mixture of that with low molecular weight species, giving a random structure. The hydrophobic polymer may also itself be a copolymer derived from two or more monomers from which the above polymers are derived.

The pharmaceutically or veterinarily acceptable hydrophilic polymer B may be, for example, polyvinyl alcohol, polyvinylpyrrolidone, polyethylene oxide, polyethylene glycol, polyacrylamide, polymethacrylamide, dextran, alginic acid, sodium alginate, gelatine or a copolymer of two or more of the monomers from which the above polymers are derived.

In a further alternative, the hydrophilic polymer B may itself be a copolymer, for example a polyoxyethylene/polyoxypropylene block copolymer of the type known as "Pluronics" (trade mark) or "Synperonics" (trade mark).

Various mechanisms by which drugs are released from biodegradable polymers are described in "Controlled Release of Biactive Materials", edited by R. Baker, Academic Press 1980, particularly chapter 1, pages 1—17, by J. Heller and R. W. Baker.

In the present invention, when the dry amphipathic copolymer, containing a polypeptide, is immersed in water or placed in an aqueous physiological environment within an animal body, water uptake is a function of the hydrophilic or water-interactive parts of the copolymer, and the material swells. This absorption of water, however, renders the water-insoluble parts of the copolymer incompatible, and these hydrophobic parts of the copolymer then serve as cross-linking points, which thus serve to limit further water uptake. In this swollen, hydrated state, the matrix is permeable to water-soluble polypeptides incorporated within the matrix, and such polypeptides are thus progressively desorbed from the matrix.

In the process of swelling, and when swollen to some equilibrium state, hydrolytic degradation of the hydrophobic part of the copolymer starts to occur. The partially degraded copolymer has greater swellability, so that continued hydrolysis leads to progressively further water uptake, an increasingly water-permeable matrix, and a further increase in polypeptide desorption which compensates for its decreasing concentration and maintains its continuous release. Thus, by appropriate design of the copolymer material, the initial swelling to a hydrogel and consequent desorption of active material, and the rate of subsequent hydrolytic degradation to increase the further desorption of active material to compensation for its decreasing concentration in the matrix, can be controlled so as to give continuous release of active material over an extended period of time, as defined above.

Such an ideal release profile for the active material can also be obtained by blending different copolymers, each having its own defined properties (for example, molecular weight, molecular weight distribution, block structure, hydrophilicity, degradation properties, diffusional properties), and by appropriate combination of different such materials, the rate of release, and the duration of release, of an active material can be varied as desired.

Also by appropriate choice of the above parameters, and/or appropriate blending, a copolymer material can be obtained which allows of processing into implants at relatively low temperatures, certainly below 100°C, and in some cases even at room temperature, and is thus suitable for the fabrication of implants incorporating heat sensitive or solvent sensitive polypeptide active materials. For example, block copolymers of polyethylene glycol and amorphous hydrophobic polymers, having a glass transition temperature above 37°C, are particularly useful, because the polyethylene glycol block plasticises the hydrophobic block, giving a material which is readily processed at relatively low, even at room temperature, while on subsequent standing the polyethylene glycol blocks crystallise to give a tough hard product which can be easily handled.

The block copolymers defined above are themselves novel, useful materials, *per se*. Thus, according to a further feature of the invention, there is provided a pharmaceutically or veterinarily acceptable amphipathic linear, branched or graft block copolymer, which has a minimum weight average molecular weight of 5,000, in which the hydrophobic component is biodegradable or hydrolytically unstable under normal physiological conditions, and the hydrophilic component may or may not be biodegradable, and which copolymer is capable of absorbing water to form a hydrogel when placed in water or an aqueous environment.

Particular such copolymers are those defined above.

According to a further feature of the invention, there is provided a blend of two or more such copolymers as defined above.

These copolymers and copolymer blends are also useful more generally for the continuous release of non-peptide drugs by oral, including intra-ruminal, parenteral, ocular, rectal or vaginal administration.

Thus, according to further features of this invention there are provided pharmaceutical or veterinary compositions comprising a non-peptide pharmacologically-active compound and a block copolymer as defined above, and the use of such block copolymers for the continuous release of such a non-peptide, pharmacologically-active compound.

According to a further feature of the invention, there is provided a process for the manufacture of a pharmaceutically or veterinarily acceptable amphipathic linear, branched or graft block copolymer as defined above, which comprises copolymerising monomer A and monomer B by conventional techniques such as graft copolymerisation, polycondensation and polyaddition, optionally with an appropriate catalyst, for example zinc oxide, zinc carbonate, basic zinc carbonate, diethyl zinc, organotin compounds, for example stannous octoate (stannous 2-ethylhexanoate), tributylaluminium, titanium, magnesium or barium compounds or litharge, and of these stannous octoate is generally preferred.

The copolymerisations are otherwise carried out in conventional manner, known in the polymer art, as regards time and temperature.

The invention is illustrated but not limited by the following Examples:—

20

Example 1

Polyethylene glycol of molecular weight 20,000 (30 g) was stirred and heated under vacuum (<0.1 mm of mercury 13.3 Pa) at 120°C for 3 hours. D,L-lactide (15 g) and glycolide (15 g) were added, and the mixture was stirred under a nitrogen atmosphere until the solids melted. The temperature was raised to 160°C, and stannous octoate (stannous 2-ethylhexanoate) (0.1 ml) was added. The mixture was maintained at 160°C for 3 hours, by which time it had become highly viscous, and it was then cooled and dissolved in acetone (200 ml). This acetone solution was added slowly to vigorously stirred ethanol (1500 ml), and the precipitate thus produced was filtered off, and dried in a vacuum oven for 3 hours at room temperature, then overnight at 40°C.

The n.m.r. spectrum of this copolymer, in deuteriochloroform, showed it to have the composition oxyethylene:lactic:glycolic of 2:1:1.

This copolymer was moulded at about 60°C to a soft, plastic transparent film. A sample (39 mg) swelled rapidly when placed in water, taking up 135 mg of water over 4 hours, to give a transparent hydrogel which subsequently disintegrated over 2 weeks at 37°C.

35

Example 2

The polymer described in Example 1 (20.2 mg) and bovine growth hormone (BGH), (5.1 mg) were blended together at about 40°C to give an opaque blend, which was moulded into a slab 1 mm thick. This slab was immersed in a buffer solution at pH 8.6 (M/15 buffer, pH 8.6, containing 0.01% sodium azide), and released a material of molecular weight about 22,000 which had the same retention time on high pressure liquid chromatography as BGH, over a period of at least 12 days.

40

Example 3

Using the process described in Example 2, the copolymer/BGH blend was formed into discs weighing about 45 mg and containing about 20% of BGH. When such discs were implanted, each in a hypophysectomised rat, the animals' weights increased by an average of 25% over 7 days, whereas the weights of control animals each given a placebo implant remained virtually unchanged.

45

Example 4

The copolymer described in Example 1 (13.5 mg) and monoclonal mouse immunoglobulin A (IgA), with a defined antigen specificity and a molecular weight of >180,000 (1.5 mg) were blended at 50°C to give a homogeneous mixture of the IgA in the copolymer, and the protein/copolymer mixture was moulded to give a sphere of ~ 2 mm diameter. The *in vitro* release of IgA was evaluated by immersing the protein copolymer in buffer (phosphate buffered saline, pH 7.2) at 37°C. Using an enzyme linked immunoassay technique the aqueous medium was assayed for active IgA, and release of the biologically active protein was shown to start after 2 days and continue for at least 9 days.

50

Example 5

Polyethylene glycol having a molecular weight of 20,000 (50 g) was dissolved in chloroform (150 mg) and washed six times with distilled water (~ 300 ml), discarding the aqueous washes. The chloroform was evaporated under reduced pressure and the purified polyethylene glycol was dried at 160°C/6.7 Pa (0.05 mm Hg) for 1 h.

60

Stannous octoate (stannous 2-ethylhexanoate) (~ 5 g) was purified by heating at 140°C/7.3 Pa (0.055 mm Hg), to remove impurities. The purified polyethylene glycol (14.3 g) was heated to 160°C under vacuum (7.3 Pa (0.05 mm Hg)) in a 100 ml round bottomed flask for 1 h. Freshly prepared, pure D,L-lactide (42.9 g)

65

was added under nitrogen and melted at 160°C. Stannous octoate (0.2 ml) was added, and the mixture was stirred until the viscosity no longer allowed stirring to continue. After 3 h, a highly viscous product was obtained. The mixture was allowed to cool, the flask was broken, the contents of the flask were dissolved in acetone (~ 300 ml) and the solution was filtered. The filtrate was added slowly to ethanol (~ 1000 ml) with vigorous agitation to give a fibrous precipitate, which was collected and dried at 30°C in a vacuum oven overnight. Analysis of the product by n.m.r. showed the product to have a composition of oxvethylene:lactic of 1:3, and the intrinsic viscosity in chloroform was 1.055.

The product was moulded to a thin (0.2 mm), soft, plastic transparent film. On immersion in water, the film (0.54 g) increased in weight to 0.95 in 1 day at 37°C. The hydrated transparent film had rigidity and strength superior to the initially dry copolymer. After 35 days, the film was intact and retained good mechanical properties showing that the copolymer was being degraded only slowly, as shown by change of composition by n.m.r.

slow degradation

When bovine growth hormone is incorporated into the dry copolymer at 60°C, the resulting polypeptide/polymer blend releases a 22000 molecular weight product into buffer (M/15 phosphate buffer, pH 8.6) over at least 7 days.

Example 6

Polyethylene glycol having a molecular weight of 6000 (50 g) was purified using the method described above in Example 5.

The purified dry polyethylene glycol (7.5 g) and stannous chloride dihydrate (15 mg) were mixed at room temperature then heated with stirring to 155°C under high vacuum (13.3—1.33 Pa i.e. 0.1—0.01 mm Hg) and maintained at this temperature for 2 h while freshly prepared, dry D,L-lactide (22.5 g) was added to the mixture under nitrogen, and melted. The reaction temperature was maintained at 155—160°C for 3 h to give a viscous product, which was poured onto poly-tetrafluoroethylene film and allowed to cool. The polymeric product was dissolved in acetone (70 ml) with warming, and the polymer was isolated by pouring the acetone solution into ethanol (600 ml). The precipitate was dried in a vacuum oven overnight at 60°C. The polymer had an intrinsic viscosity in chloroform of 0.41. When pressed as a thin film (0.2 mm) and immersed in water, the polymer takes up approximately its own weight of water at 37°C over 24 h to give a tough hydrogel.

Example 7

99 mg of a block copolymer as prepared in Example 6 containing 25 parts of polyethylene glycol (mol. wt. 6000) and 75 parts of poly(D,L-lactide) was dissolved in 4.5 ml of anhydride free glacial acetic acid and 0.5 ml of distilled water. 200 µl of a solution containing 1.1 mg of mouse epidermal growth factor (EGF) was added to the polymer solution, and the mixture was homogenised. The homogenised solution was frozen and then freeze dried for 18 h, the product was moulded at 50°C to give an implant weighing 40 mg (~ 8 mm x 4 mm x 1 mm). The implant was placed in 1 ml of human serum at 37°C, and the release of EGF was measured by radio immunoassay on aliquots of serum. The results showed a continuous release of peptide over at least three days.

Example 8

25 g of a copolymer containing equimolar proportions of D,L-lactide and glycolide and having an intrinsic viscosity in chloroform of 0.20 was dissolved in 50 ml of dry ethyl acetate, and the solution was heated to reflux with stirring under nitrogen. 0.25 g of lauroyl peroxide was dissolved in freshly distilled vinyl pyrrolidone (25 ml). The mixture was added dropwise to the refluxing polymer over 2 h, and the mixture was heated at reflux for a further 6 h. On cooling, the mixture gelled. Purification of the amphipathic block graft copolymer by removal of homo polymer of polyvinyl pyrrolidone using preparation techniques was difficult as precipitation often resulted in colloidal suspensions, and this indicated that grafting of polyvinyl pyrrolidone to the lactide/glycolide copolymer had occurred.

The ethyl acetate mixture was therefore warmed to 70°C and 50 ml of ethanol was added to give a colloidal suspension, from which the polymer was isolated by precipitation into n-hexane (2 litres). The polymer thus obtained was dried at 50°C overnight under vacuum to give on cooling a brittle product consisting of graft copolymer and homo polyvinylpyrrolidone. The product had an intrinsic viscosity of 0.29 in chloroform, and approximately 50% of polyvinyl-pyrrolidone as homopolymer and graft block copolymer.

The polymer thus obtained (0.45 g) and ICI 118,630 (0.05 g) were dissolved in anhydride-free glacial acetic acid (5 ml) and freeze dried at 1.33 Pa (0.01 mm of mercury) for 22 h.

The product was moulded at 110°C for 20 s to give a slab (~ 0.8 cm x 1.2 mm x 2 mm, weighing 30 mg) which, when immersed in aqueous pH 7.4 buffer at 37°C released the peptide over a period of several days.

PGCLA
PVP
graft vinyl polymer
(peroxide)

Example 9

50 g of polyvinyl alcohol having a molecular weight of 14,000 was dissolved in 500 g of commercial D,L-lactic acid (containing ~ 12% water) with stirring under nitrogen. The mixture was heated to 140°C and water was distilled off over 8 h, during which time the mixture became progressively more viscous and its temperature rose to 190°C. When no further water distilled over, the pressure was reduced to ~ 25 cm of

PVA derivative

mercury, and the mixture was heated for a further 8 h. Finally, the pressure was reduced to 13.3 Pa (0.1 mm of mercury) and the mixture was heated at 200°C for 8 h to give a highly viscous amber product.

The polymer was allowed to cool, and the flask was broken. The product was broken up into small pieces and dissolved in methanol (1.5 litres), and the product was isolated by precipitation in 10 litres of distilled water. The precipitation was washed with a further 5 litres of water, and dried under vacuum at room temperature for 8 h, finally at 100°C for 16 h, to give an amber glassy product which consisted of a polyvinyl alcohol backbone containing pendant polylactic acid chains of low molecular weight, intrinsic viscosity = 0.55 in chloroform. The product contained approximately 85% of polylactic acid, and the pendant polylactic acid average chain length was approximately 3.5.

The polymer was moulded at 100°C to give a slab 1 cm x 0.2 cm x 0.2 cm which was immersed in water at 37°C. The product absorbed water and became flexible, and eroded to give soluble products over a period of 2 months.

Example 10

Mouse epidermal growth factor (285 µl of a 21 mg/ml solution in distilled water) was added to a solution of an 80/20 poly(D,L-lactide)/PEG 6000 copolymer of intrinsic viscosity 0.36 in chloroform, (45 mg) in 2.5 ml of 90% aqueous acetic acid. The solution of peptide and polymer was frozen and then freeze dried at 1.3 Pa (0.01 mm Hg) for 24 hours to give a dried product. The freeze dried material was moulded at 60°C to give implants weighing 13.5 mg and 15.3 mg containing 1.3 and 1.5 mg of peptide respectively.

These were implanted subcutaneously into 2 cats, each fitted with a gastric fistula. Blood samples were taken, and gastric acid output in response to a histamine stimulus was measured. Peptide was detected in the blood by radioimmunoassay for a minimum of 3 days subsequent to implantation, and gastric acid output showed inhibition of 3—6 days subsequent to implantation.

Example 11

Mouse epidermal growth factor (120 µl of 10.5 mg peptide in 320 l of distilled water) was added to a solution of an 85/15 poly(D,L-lactide)/PEG 6000 copolymer of intrinsic viscosity 0.39 in chloroform, (36 mg) in 1.8 ml of 90% aqueous acetic acid. The resultant solution was frozen and freeze-dried overnight. The freeze dried material was moulded at 70°C to give an implant weighing 16.9 mg (dimensions approximately 1 x 1 x 5 mm).

Peptide was released from this implant continuously over at least 15 days into 10% human serum in water containing 0.1% sodium azide.

Example 12

To show the effect of composition and hydrophilicity of the block copolymer on release of polypeptide from implants the following comparison was carried out.

In separate experiments implants were prepared using

(a) a block copolymer of intrinsic viscosity 0.39 in chloroform containing 25% w/w polyethylene glycol having a molecular weight of 6000 and 75% w/w of poly(D,L-lactide).

(b) a block copolymer of intrinsic viscosity 0.79 in chloroform containing 5% w/w polyethylene glycol having a molecular weight of 6000 and 95% w/w of poly(D,L-lactide).

76.2 mg of polymer and ICI 118,630 (23.8 mg as the acetate salt, equivalent to 20 mg pure peptide) were dissolved in anhydride-free glacial acetic acid (1.5 ml). The solution was frozen and freeze dried for 18 hours, and the freeze dried product was moulded at ~ 70°C to give implants weighing ~ 45—50 mg (dimensions approximately 0.2 cm x 0.2 cm x 1 cm).

The implants were immersed in 1 ml of McIntains pH 7.4 buffer at 37°C, and 1 ml samples of the aqueous medium were removed at given time points and assayed by high pressure liquid chromatography for drug content. The aqueous medium removed was replaced each time by 1 ml of fresh buffer.

These release experiments showed that implants prepared using the more hydrophilic polymer, containing 25% polyethylene glycol, released compounds for ~ 18 days.

In contrast, the implant prepared using the less hydrophilic copolymer, containing 5% polyethylene glycol, released compound continuously for at least 25 days.

Example 13

Poly(ethylene glycol methyl ether) having a molecular weight of 5000 was purified as in Example 5.

20 g of the purified poly(ethylene glycol methyl ether) was dried at 160°C/1.3 Pa (0.01 mm Hg) for 1 hour. 80 g of dry, freshly prepared D,L-lactide were added and the mixture stirred under a nitrogen atmosphere at 160°C. When all the D,L-lactide had melted, 0.15 ml of stannous octoate (stannous-2-ethylhexanoate) were added, and the mixture was maintained at 160°C for 6 hours, during which time a highly viscous product was formed. The mixture was allowed to cool, the flask was broken and the contents were dissolved in 200 ml of acetone. The acetone solution of polymer was added with vigorous stirring to 2000 ml of hexane to precipitate the polymer. The precipitated polymer was dried at 70°C under reduced pressure for 24 hours to give a block copolymer having an AB structure where A is polylactic acid and B is poly(ethylene glycol methyl ether).

This copolymer is particularly useful for preparing water-in-oil dispersions, which can be used to

prepare microcapsules, or in microencapsulation procedures.

For example, 5 g of the copolymer was dissolved in 200 ml of methylene chloride, and 1 ml of an aqueous solution of ICI 118,530 containing 20 mg of compound was added with vigorous stirring, to produce a stable water in oil dispersion.

The water-in-oil emulsion was stirred vigorously and a non-solvent, such as hexane (2000 ml) was added slowly to produce microcapsules, which were isolated by filtration, and dried, to give a drug/polymer mixture which even in this microcapsule or microencapsulated form gives sustained release over a period of several days.

The poly(ethylene glycol methyl ether) used in the above process was replaced by other derivatives of poly(ethylene glycol) to prepare similar block copolymers, and suitable examples are the monocetyl ethers (ceto macrogols) and stearate esters.

Claims


1. A pharmaceutical composition comprising a pharmacologically useful polypeptide and a pharmaceutically or veterinarily acceptable, amphipathic, non-cross-linked linear, branched or graft block copolymer, which has a minimum weight average molecular weight of 5,000, in which the hydrophobic component is biodegradable or hydrolytically unstable under normal physiological conditions, and the hydrophilic component may or may not be biodegradable, the composition being capable of absorbing water to form a hydrogel when placed in water or an aqueous physiological-type environment in an animal body, but excluding such compositions in which the hydrophobic component is derivable from at least one cyclic (thio) ether.

2. A composition as claimed in claim 1 wherein the pharmacologically useful polypeptide is selected from oxytocin, vasopressin, adrenocorticotrophic hormone, epidermal growth factor, prolactin, luteinising hormone releasing hormone, growth hormone, growth hormone releasing factor, insulin, somatostatin, glucagon, interferon, gastrin, tetragastrin, pentagastrin, urogastrone, secretin, calcitonin, enkephalins, endorphins, angiotensins, renin, bradykinin, bacitracins, polymyxins, colistins, tyrocidin, gramicidines, and synthetic analogues, modifications and pharmacologically active fragments thereof, monoclonal antibodies and soluble vaccines.


3. A composition as claimed in claim 1 wherein the poly-peptide is $\text{[Glu-His-Trp-Ser-Tyr-D-Ser(O-tBu)-Leu-Arg-Pro-Azgly-NH}_2\text{]}$.

4. A composition as claimed in claim 1, 2 or 3 wherein the pharmaceutically or veterinarily acceptable amphipathic copolymer is a linear block copolymer of the formula $A_m(BA)_n$ or $B_m(AB)_n$ wherein m is 0 or 1, n is an integer, A is a pharmaceutically or veterinarily acceptable hydrophobic polymer and B is a pharmaceutically or veterinarily acceptable hydrophilic polymer, or the amphipathic copolymer is a graft or branched block copolymer of the formula AB_n or BA_n wherein A, B and n have the meanings stated above and wherein respectively either A or B is a backbone polymer with n units of a monomer or polymer B or A respectively grafted onto it.


5. A composition as claimed in claim 4 wherein the pharmaceutically or veterinarily acceptable hydrophobic polymer A is selected from poly(D-, L- and DL-lactic acids), poly(D-, L- and DL-lactides), polyglycolic acid, polyglycolide, poly-L-caprolactone, poly(3-hydroxybutyric acid), non-therapeutic hydrophobic polypeptides, polyacetals of the formula:—



wherein R is a hydrocarbon radical and n has the meaning stated above, polycarbonates or polyorthoesters of the formula:—



wherein R and n have the meaning stated above, and copolymers of the formula:—




wherein R and n have the meanings stated above, and copolymers derived from two or more monomers from which the above polymers are derived; and the pharmaceutically or veterinarily acceptable hydrophilic polymer B is selected from polyvinyl alcohol, polyvinylpyrrolidone, polyethylene oxide, polyethylene glycol, polyacrylamide, polymethacrylamide, dextran, alginic acid, sodium alginate, and gelatine, copolymers of two or more of the monomers from which the above polymers are derived, and polyoxyethylene/polyoxypropylene block copolymers.

6. A pharmaceutically or veterinarily acceptable amphipathic, non-cross-linked linear, branched or graft block copolymer, which has a minimum weight average molecular weight of 5,000, in which the hydrophobic component is biodegradable or hydrolytically unstable under normal physiological conditions, and the hydrophilic component may or may not be biodegradable, the copolymer being capable of absorbing water to form a hydrogel when placed in water or an aqueous physiological-type environment in an animal body.

7. A copolymer as claimed in claim 6 wherein the pharmaceutically or veterinarily acceptable amphipathic copolymer is a linear block copolymer of the formula $A_m(BA)_n$ or $B_m(AB)_n$, wherein m is 0 or 1, n is an integer, A is a pharmaceutically or veterinarily acceptable hydrophobic polymer and B is a pharmaceutically or veterinarily acceptable hydrophilic polymer, or the amphipathic copolymer is a graft or branched block copolymer of the formula AB_n or BA_n , wherein A, B and n have the meanings stated above and wherein respectively either A or B is a backbone polymer with n units of a monomer or polymer B or A respectively grafted onto it.


8. A copolymer as claimed in claim 7 wherein the pharmaceutically or veterinarily acceptable hydrophobic polymer A is selected from poly(D-, L- and DL-lactic acids), poly(D-, L- and DL-lactides), polyglycolic acid, polyglycolide, poly-ε-caprolactone, poly(3-hydroxybutyric acid), non-therapeutic hydrophobic polypeptides, polyacetals of the formula:—




wherein R is a hydrocarbon radical.



represents two alkyl radicals or a cycloalkyl ring, and n is an integer, polycarbonates or polyorthoesters of the formula:—



wherein R and n have the meanings stated above and the arcuate dotted line represents a hydrocarbon linking group, and copolymers of the formula:—



wherein R and n have the meanings stated above, and copolymers derived from two or more monomers from which the above polymers are derived; and the pharmaceutically or veterinarily acceptable hydrophilic polymer B is selected from polyvinyl alcohol, polyvinylpyrrolidone, polyethylene oxide, polyethylene glycol, polyacrylamide, polymethacrylamide, dextran, alginic acid, sodium alginate, and gelatine, and copolymers of two or more of the monomers from which the above polymers are derived, and polyoxyethylene/polyoxypropylene block copolymers.

9. A process for the manufacture of a copolymer as claimed in claim 7 which comprises copolymerising monomer or polymer A and monomer or polymer B by graft copolymerisation, polycondensation or polyaddition.

10. A pharmaceutical or veterinary composition comprising a non-peptide, pharmacologically active compound and a copolymer as claimed in claim 6.

Patentansprüche


1. Pharmazeutische Zusammensetzung, enthaltend ein pharmakologisch nützliches Polypeptid und ein pharmazeutisch oder tierarzneilich zulässiges, amphipathisches, nichtvernetztes lineares, verzweigtes oder Pfropfblockcopolymer, welches ein kleinstes Gewichtsmittel des Molekulargewichts von 5000 aufweist, in welchem die hydrophobe Komponente unter normalen physiologischen Bedingungen biologisch abbaubar oder hydrolytisch instabil ist, und in welchem die hydrophile Komponente biologisch abbaubar sein kann oder auch nicht, wobei die Zusammensetzung fähig ist, Wasser unter Bildung eines Hydrogels zu absorbieren, wenn sie in Wasser oder eine wäßrige Umgebung physiologischer Art in einem Tierkörper angeordnet wird, wobei jedoch solche Zusammensetzungen ausgeschlossen sind, bei denen die hydrophobe Komponente sich von mindestens einem cyclischen (Thio)-ether ableitet.

2. Zusammensetzung nach Anspruch 1, bei welcher das pharmakologisch nützliche Polypeptid ausgewählt ist aus Oxytocin, Vasopressin, adrenocorticotrophem Hormon, epidermischem Wachstumsfaktor, Prolactin, Luliberin oder Luteinisierungshormon freisetzendem Hormon, Wachstumshormon, Wachstumshormon freisetzendem Faktor, Insulin, Somatostatin, Glucagon, Interferon, Gastrin, Tetragastrin, Pentagastrin, Urogastron, Secretin, Calcitonin, Enkephalinen, Endorphinen, Angiotensinen, Renin, Bradykinin, Bacitracinen, Polymyxinen, Colistinen, Tyrocidin, Gramicidinen und synthetischen Analogen, Modifikationen und pharmakologisch aktiven Fragmenten davor, monoclonalen Antikörpern und löslichen Vaccinen.


3. Zusammensetzung nach Anspruch 1, bei welcher das Polypeptid das folgende ist: $\text{Glu-His-Trp-Ser-Tyr-D-Ser(O-tBu)-Leu-Arg-Pro-Azgly-NH}_2$.

4. Zusammensetzung nach Anspruch 1, 2 oder 3, bei welcher das pharmazeutisch oder tierarzneilich zulässige amphipathische Copolymer ein lineares Blockcopolymer der Formel $A_m(BA)_n$ oder $B_m(AB)_n$ ist, worin m für 0 oder 1 steht, n für eine Ganzzahl steht, A für ein pharmazeutisch oder tierarzneilich zulässiges hydrophobes Polymer steht und B für ein pharmazeutisch oder tierarzneilich zulässiges hydrophiles Polymer steht, oder worin das amphipathische Copolymer ein Pfropf- oder verzweigtes Copolymer der Formel AB_n oder BA_n ist, worin A, B und n die oben angegebenen Bedeutungen besitzen und worin entweder A oder B ein Gerüstpolymer ist, auf das n Einheiten eines Monomers oder Polymers B bzw. A aufgepfropft sind.


5. Zusammensetzung nach Anspruch 4, in welcher das pharmazeutisch oder tierarzneilich zulässige hydrophobe Polymer A ausgewählt ist aus Poly(D-, L- und DL-milchsäuren), Poly(D-, L- und DL-lactiden), Polyglycolsäure, Polyglycolid, Poly-ε-caprolacton, Poly(3-hydroxybuttersäure), nichttherapeutischen hydrophoben Polypeptiden, Polyacetalen der Formel



worin R für ein Kohlenwasserstoffradikal steht und n die oben angegebene Bedeutung besitzt, Polycarbonaten oder Polyoxyestern der Formel



worin R und n die oben angegebenen Bedeutungen besitzen, und Copolymeren der Formel




worin R und n die oben angegebenen Bedeutungen besitzen, und Copolymeren, die sich von zwei oder mehr Monomeren ableiten, von denen die obigen Polymere sich ableiten; und das pharmazeutisch oder tierarzneilich zulässige hydrophile Polymer B ausgewählt ist aus Polyvinylalkohol, Polyvinylpyrrolidon, Polyethylenoxid, Polyethylenglycol, Polyacrylamid, Polymethacrylamid, Dextran, Alginsäure, Natriumalginate und Gelatine, Copolymeren aus zwei oder mehr der Monomeren, von denen sich die obigen Polymere ableiten, und Polyoxyethylen/Polyoxypropylen-Blockcopolymeren.

6. Pharmazeutisch oder tierarzneilich zulässiges amphipathisches, nicht-vernetztes lineares, verzweigtes oder Pfropfblockcopolymer, welches ein kleinstes Gewichtsmittel des Molekulargewichts von 5000 aufweist, worin die hydrophobe Komponente unter normal physiologischen Bedingungen biologisch abbaubar oder hydrolytisch instabil ist, und die hydrophile Komponente biologisch abbaubar oder auch nicht sein kann, wobei das Copolymer fähig ist, Wasser unter Bildung eines Hydrogels zu absorbieren, wenn es in Wasser oder einer wäßrigen Umgebung physiologischer Art in einem Tierkörper angeordnet ist.

7. Copolymer nach Anspruch 6, bei welchem das pharmazeutisch oder tierarzneilich zulässige amphipathische Copolymer ein lineares Blockpolymer der Formel $A_m(BA)_n$ oder $B_m(AB)_n$ ist, worin m für 0 oder 1 steht, n für eine Ganzzahl steht, A für ein pharmazeutisch oder tierarzneilich zulässiges hydrophobes Polymer steht und B für ein pharmazeutisch oder tierarzneilich zulässiges hydrophiles Polymer steht, oder das amphipathische Copolymer ein Pfropf- oder verzweigtes Blockcopolymer der Formel AB_n oder BA_n ist, worin A, B und n die oben angegebenen Bedeutungen besitzen und worin entweder A oder B ein Gerüstpolymer ist, auf das n Einheiten eines Monomers oder Polymers B bzw. A aufgefropft sind.


8. Copolymer nach Anspruch 7, bei welchem das pharmazeutisch oder tierarzneilich zulässige hydrophobe Polymer A ausgewählt ist aus Poly(D-, L- und DL-milchsäuren), Poly(D-, L- und DL-lactiden), Polyglycolsäure, Polyglycolid, Poly-ε-caprolacton, Poly(3-hydroxybuttersäure), nicht-therapeutischen hydrophoben Polypeptiden, Polyacetalen der Formel




worin R für ein Kohlenwasserstoffradikal steht und



für zwei Alkylradikale oder einen Cycloalkylring steht, und n für eine Ganzzahl steht, Polycarbonaten oder Polyorthoestern der Formel



worin R und n die oben angegebenen Bedeutungen besitzen und die gekrümmte gestrichelte Linie für eine Kohlenwasserstoffbrückengruppe steht, und Copolymeren der Formel



worin R und n die oben angegebenen Bedeutungen besitzen, und Copolymeren, die sich von zwei oder mehr Monomeren ableiten, von denen die obigen Polymeren sich ableiten; und das pharmazeutisch oder tierarzneilich zulässige hydrophile Polymer B ausgewählt ist aus Polyvinylalkohol, Polyvinylpyrrolidon, Polyethylenoxid, Polyethylenglycol, Polyacrylamid, Polymethacrylamid, Dextran, Alginsäure, Natriumalginate und Gelatine und Copolymeren aus zwei oder mehr der obigen Monomeren, von denen sich die obigen Polymere ableiten, und Polyoxyethylen/Polyoxypropylen-Blockcopolymeren.

9. Verfahren zur Herstellung eines Copolymeren nach Anspruch 7, bei welchem ein Polymer A und ein Monomer oder Polymer B durch Pfropfcopolymerisation, Polykondensation oder Polyaddition copolymerisiert werden.

10. Pharmazeutische oder tierarzneiliche Zusammensetzung, welche eine nicht peptidische, pharmakologisch aktive Verbindung und ein Copolymer nach Anspruch 6 enthält.

Revendications

1. Composition pharmaceutique comprenant un polypeptide utile du point de vue pharmacologique et un copolymère non réticulé, linéaire, ramifié ou séquence greffé, amphipathique, acceptable du point de vue pharmaceutique ou vétérinaire, qui possède une moyenne minimale en poids du poids moléculaire égale à 5000, composition dans laquelle le constituant hydrophobe est biodégradable ou instable à l'hydrolyse dans des conditions physiologiques normales, et le constituant hydrophile peut être ou non biodégradable, la composition étant capable d'absorber de l'eau pour former un hydrogel lorsqu'elle est placée dans de l'eau ou un environnement aqueux de type physiologique présent dans le corps d'un animal, mais en excluant de telles compositions dans lesquelles le constituant hydrophobe peut être obtenu à partir d'au moins un (thio)-éther cyclique.


2. Composition suivant la revendication 1, dans laquelle le polypeptide utile du point de vue pharmacologique est choisi entre l'ocytocine, la vasopressine, l'hormone adrénocorticotrophique, le facteur de croissance épidermique, la prolactine, la lutibérine ou l'hormone de libération de l'hormone lutéinisante, l'hormone de croissance, le facteur de libération de l'hormone de croissance, l'insuline, la somatostatine, le glucagon, l'interféron, la gastrine, la tétragastrine, la pentagastrine, l'urogastrone, la sécrétine, la calcitonine, des enképhalines, des endorphines, des angiotensines, la rénine, la bradykinine, des bacitracines, des polymyxines, des colistines, la tyrocidine, des gramicidines, et leurs substances synthétiques analogues, leurs variantes et leurs fragments pharmacologiquement actifs, des anticorps monoclonaux et des vaccins solubles.

3. Composition suivant la revendication 1, dans laquelle le polypeptide est $\text{Glu-His-Trp-Ser-Tyr-D-Ser(O-tBu)-Leu-Arg-Pro-Azgly-NH}_2$.


4. Composition suivant la revendication 1, 2 ou 3, dans laquelle le copolymère amphipathique acceptable du point de vue pharmaceutique ou vétérinaire, est un copolymère séquence linéaire répondant à la formule $A_m(BA)_n$ ou $B_n(AB)_m$, dans laquelle m a la valeur 0 ou 1, n est un nombre entier, A est un polymère hydrophobe acceptable du point de vue pharmaceutique ou vétérinaire et B est un polymère hydrophile acceptable du point de vue pharmaceutique ou vétérinaire, ou bien le copolymère amphipathique est un copolymère greffé ou séquence ramifié répondant à la formule AB_n ou BA_n , dans laquelle A, B et n répondent aux définitions précitées et dans laquelle, respectivement, A ou bien B est un

squelette polymérique portant respectivement n motifs d'un monomère ou polymère B ou A fixé par greffage.


5. Composition suivant la revendication 4, dans laquelle le polymère hydrophobe A acceptable du point de vue pharmaceutique ou vétérinaire est choisi entre des poly-(acides D-, L- et DL-lactiques), des poly-(D-, L- et DL-lactides), l'acide polyglycolique, un polyglycolide, la poly-ε-caprolactone, le poly(acide 3-hydroxybutyrique), des polypeptides hydrophobes dépourvus d'activité thérapeutique, des polyacétals répondant à la formule:



20 dans laquelle R est un radical hydrocarboné et n répond à la définition précitée, des polycarbonates ou des polyorthoesters répondant à la formule:



30 dans laquelle R et n répondent aux définitions précitées, et des copolymères répondant à la formule:




45 dans laquelle R et n répondent aux définitions précitées, et des copolymères dérivés deux ou plus de deux monomères, desquels dérivent les polymères précités; et le polymère hydrophile B acceptable du point de vue pharmaceutique ou vétérinaire est choisi entre l'alcool polyvinylique, la polyvinylpyrrolidone, l'oxyde de polyéthylène, un polyéthylène-glycol, un polycrylamide, un polyméthacrylamide, le dextrane, l'acide alginique, l'alginate de sodium et la gélatine, des copolymères constitués de deux ou plus de deux des monomères desquels dérivent les polymères précités, et des copolymères séquencés polyoxyéthylène/polyoxypropylène.

50 6. Copolymère non réticulé linéaire, ramifié ou séquencé greffé, amphipathique, acceptable du point de vue pharmaceutique ou vétérinaire, qui possède une moyenne minimale en poids du poids moléculaire égale à 5000, dans lequel le constituant hydrophobe est biodégradable ou instable par hydrolyse dans des conditions physiologiques normales, et le constituant hydrophile peut être ou non biodégradable, le copolymère étant capable d'absorber de l'eau pour former un hydrogel lorsqu'il est placé dans de l'eau ou un environnement aqueux de type physiologique présent dans le corps d'un animal.

55 7. Copolymère suivant la revendication 6, dans lequel le copolymère amphipathique acceptable du point de vue pharmaceutique ou vétérinaire est un copolymère séquencé linéaire répondant à la formule $A_m(BA)_n$ ou $B_m(AB)_n$, dans laquelle m a la valeur 0 ou 1, n est un nombre entier, A est un polymère hydrophobe acceptable du point de vue pharmaceutique ou vétérinaire et B est un polymère hydrophil acceptable du point de vue pharmaceutique ou vétérinaire, ou bien le copolymère amphipathique est un copolymère séquencé, greffé ou ramifié, répondant à la formule AB_n ou BA_n , dans laquelle A, B et n répondent aux définitions précitées et dans lequel, respectivement, A ou B est un squelette polymérique portant respectivement n motifs d'un monomère ou polymère B ou A, fixé par greffage.

60 8. Copolymère suivant la revendication 7, dans lequel le polymère hydrophobe A acceptable du point de vue pharmaceutique ou vétérinaire est choisi entre des poly-(acides D-, L- et DL-lactiques), des poly-(D-, L- et DL-lactides), l'acide polyglycolique, un polyglycolide, la poly-ε-caprolactone, le poly(acide 3-hydroxy-


butyrique), des polypeptides hydrophobes dépourvus d'activité thérapeutique, des polyacétals répondant à la formule:




dans laquelle R est un radical hydrocarboné,



représente deux radicaux alkyle ou un noyau cycloalkyle, et n est un nombre entier, des polycarbonates ou des polyorthoesters répondant à la formule:



dans laquelle R et n répondent aux définitions précitées et la ligne arquée en pointillés représente un groupe hydrocarboné de jonction, et des copolymères répondant à la formule:



dans laquelle R et n répondent aux définitions précitées, et des copolymères dérivés de deux ou plus de deux monomères desquels dérivent les polymères précités: et le polymère hydrophile B acceptable du point de vue pharmaceutique ou vétérinaire est choisi entre l'alcool polyvinylique, la polyvinylpyrrolidone, l'oxyde de polyéthylène, un polyéthylène-glycol, un polyacrylamide, un polyméthacrylamide, le dextrane, l'acide alginique, l'alginate de sodium et la gélatine, des copolymères constitués de deux ou plus de deux des monomères desquels dérivent les polymères précités, et des copolymères séquencés polyoxyéthylène/polyoxypropylène.

9. Procédé de production d'un copolymère suivant la revendication 7, qui consiste à copolymériser un monomère ou polymère A et un monomère ou polymère B par copolymérisation par greffage, polycondensation ou polyaddition.

10. Composition pharmaceutique ou vétérinaire comprenant un composé non peptidique doué d'activité pharmacologique et un copolymère suivant la revendication 6.